

平鋼 (FB)

板厚	3	4.5	6	9	12	16	19	22	25	28	32	36	38
幅/長	質量	質量	質量	質量	質量	質量	質量	質量	質量	質量	質量	質量	質量
13	0.306	0.459	0.612										
16	0.377	0.565	0.754	1.13									
19	0.447	0.671	0.895	1.34									
22	0.518	0.777	1.04	1.55	2.07								
25	0.589	0.883	1.18	1.77	2.36	3.14							
32	0.754	1.13	1.51	2.26	3.01	4.02	4.77						
38	0.895	1.34	1.79	2.68	3.58	4.77	5.67	6.56	7.46				
44	1.04	1.55	2.07	3.11	4.14	5.53	6.56	7.60					
50	1.18	1.77	2.36	3.53	4.71	6.28	7.46	8.64	9.81	11.0	12.6	14.1	14.9
60		2.12	2.83	4.24	5.65	7.54	8.95						
65	1.53	2.30	3.06	4.59	6.12	8.16	9.69	11.2	12.8	14.3	16.3	18.4	19.4
70			3.30	4.95	6.59	8.79	10.4	12.1					
75	1.77	2.65	3.53	5.30	7.06	9.42	11.2	13.0	14.7	16.5	18.8	21.2	22.4
80			3.77	5.65	7.54	10.0	11.9	13.8	15.7				
90	2.12	3.18	4.24	6.36	8.48	11.3	13.4	15.5	17.7		22.6		
100	2.36	3.53	4.71	7.06	9.42	12.6	14.9	17.3	19.6	22.0	25.1	28.3	29.8
110			5.18	7.77	10.4	13.8	16.4	19.0					
120					11.3								
125	2.94	4.42	5.89	8.83	11.8	15.7	18.6	21.6	24.5	27.5	31.4	35.3	
150	3.53	5.30	7.06	10.6	14.1	18.8	22.4	25.9	29.4	33.0	37.7		44.7
160			7.54	11.3	15.1	20.1							
165			7.77	11.7	15.5	20.7							
170			8.01	12.0	16.0	21.4							
175			8.24	12.4	16.5	22.0	26.1						
180			8.48	12.7	17.0	22.6	26.8	31.1					
190			8.95	13.40	17.90	23.9							
200			9.42	14.1	18.8	25.1	29.8	34.5	39.2	44.0	50.2	56.5	
230			10.8	16.2	21.7	28.9							
250			11.8	17.7	23.6	31.4	37.3	43.2	49.1	55.0	62.8	70.6	
285				20.1	26.8								
300			14.1	21.2	28.3	37.7	44.7	51.8	58.9	65.9	75.4	84.8	
350				24.7	33.0	44.0	52.2	60.4	68.7	76.9	87.9	98.9	
400				28.3	37.7	50.2	59.7	69.1	78.5				

